

TadelaktPro™

Technical data sheet/10-2015

Decorative wall plaster

Manufacturer	CLAYLIME sprl Avenue Monplaisir, 77 BE 1030 BRUSSELS BELGIUM
Ingredients	hydraulic lime, hydrated lime, silica and other fine adjuvants.
Destination	waterproof finish for bathroom walls, ceiling, and other wet areas, for interior and protected outside walls
Classification	Fire classification MO
Appearance	White lime based powder, traditional tadelakt appearance, waterproof
Density	1,15 kg/L
VOC	not applicable
Rendement	2 kg/m ²
Drying time (at 20°C et 65% HR)	24 hours minimum
Conservation	12 months in original packaging. Frost, heat and humidity free storage
Preparation/mixture	2,8L of water for 10 kg of powder - see instructions of use
Application and supports	in accordance with DTU 59.1 - see instructions of use
Preparation of the support	See instructions of use In accordance with DTU 59.1
Security	Not classified as hazardous. See the safety data sheet

All instructions and technical details reflect our experience of the product and are provided as information only – they are not legally binding. This document contains information given in good faith based on the current state of our knowledge. They are indicative only and does not imply, therefore, any commitment on our part regarding the conditions under which our products are transported, stored, handled or used by our customers, and in case of infringement to rights belonging to third parties because of the use of our products. ClayLime warrants that its products comply with its sales specifications. This information should not be a substitute for necessary prior tests to ensure product suitability for a given use. Users are responsible for ensuring compliance with local legislation and obtain the necessary authorizations and approvals. Users are advised to check that they have the latest version of this document, ClayLime being at their disposal to provide any further information.